

# TECHNICAL DATA SHEET

## 1. IDENTIFICATION OF THE PRODUCT AND THE COMPANY

---

<b>NAME OF THE PRODUCT</b>	Textured plastic spray fine 400ml
<b>CODE</b>	110070 (Black) 110071 (Dark grey)
<b>DISTRIBUTOR</b>	BOSSAUTO INNOVA, S.A.
<b>ADDRESS</b>	c/ Thomas Edison 16, Apartado de correos 95
<b>CITY</b>	08430 La Roca del Vallés (Barcelona)
<b>PHONE</b>	902 100 667
<b>FAX</b>	902 363 047
<b>E-MAIL</b>	<a href="mailto:info@bossauto.com">info@bossauto.com</a>
<b>WEB</b>	<a href="http://www.bossauto.com">www.bossauto.com</a>

## 2. DESCRIPTION

---

Textured Plastic Spray fine is a product based on acrylic resins and special rheological additives. This product can be used for touching up structured plastic bumpers and parts. The original structure can be imitated. Texture plastic spray is a fast-drying paint with good adhesion. This product can be sprayed directly onto most plastic surfaces without using a primer. For the correct color, textured plastic spray coating can be over painted (sprayed) with the most common bumper paints.

### A. Yield

400 ml for 1-2 m<sup>2</sup>.

### B. Coverage

Dependent on the film thickness: 1 to 2 layers.

## 3. APPLICATION

---

1. Free the surface of dirt, grease etc.; let it dry.
2. Cover the parts which should not to be painted.
3. Shake the aerosol well before use during 2 to 3 minutes.
4. Spray the paint on a test surface.
5. Spray from a distance of approximately 25 cm. The structure can be influenced by changing the distance, increasing layer thickness, or by using a different actuator.

### A. Drying times

Dust dry appr. 1 hour  
Tack free appr. 3 hours  
Dry after 12 hours

\*Drying time depends on structure (film thickness)

#### 4. TECHNICAL INFORMATION

Resin	Acrylic
Pigments	Lead-free
Solids	25% (m/m)
Recommended film thickness	100 to 500 micron wet, depending on the wanted structure
Gloss	Semi-gloss to glossy, depending on layer thickness and structure
Density	0.80 kg/l
Particle size	10 - 75 micron
Colors	Black, dark grey
Thinner	Acetone
Storage	Cool and dry

The information contained herein has been obtained as the result of testing and development work carried out by us. However, this product can be put to numerous uses under widely varying circumstances and conditions and accordingly we do not guarantee the accuracy of the contents of the statements contained herein, and in particular, we do not warrant that this product is suitable for any particular use. We shall not be liable in any way whatsoever to any person who relies upon the statements contained herein without taking sufficient steps to ensure in advance that the product is suitable for this particular purpose, production, conditions and/or use.