

# TECHNICAL DATA SHEET

## 1. IDENTIFICATION OF THE PRODUCT AND THE COMPANY

<b>NAME OF THE PRODUCT</b>	C900 Contact adhesive spray 500 ml
<b>CODE</b>	110006
<b>DISTRIBUTOR</b>	BOSSAUTO INNOVA, S.A.
<b>ADDRESS</b>	c/ Thomas Edison 16, Apartado de correos 95
<b>CITY</b>	08430 La Roca del Vallés (Barcelona) SPAIN
<b>PHONE</b>	+ 34 93 860 49 23
<b>FAX</b>	+34 93 871 23 36
<b>E-MAIL</b>	<a href="mailto:info@bossauto.com">info@bossauto.com</a>
<b>WEB</b>	<a href="http://www.bossauto.com">www.bossauto.com</a>

## 2. PRODCUT DESCRIPTION

Contact adhesive in spray format. Permanent fixing, it allows to join parts together in the very first moments. Useful for: wood, leather, imitation leather, PVC, cardboard, foams, textiles, carpets, etc.

## 3. APPLICATIONS

Paper cardboard, wood textile, cork leather, various types of plastic.

## 4. PRODUCT CHARACTERISTICS

- Suitable to glue large surfaces
- Fast drying
- User-friendly
- Spray pattern about 10 centimeter wide

## 5. PHYSICAL AND CHEMICAL CHARACTERISTICS

Contents	500 ml
Basis	Synthetic resin
VOC-content	Approximately 83% w/w
Colour	Transparent white
Scent	Characteristic
Relative density at 20°C	0,75 g/ml
Yield	1,2 g/sec
Vapour pressure at 20°C	3 to 4 bar
Heat resistant	To 80°C

## **6. USAGE**

---

Before use, carefully read the directions on the packaging and act accordingly.

The surface should be clean, dry and free of grease. The aerosol should have room temperature.

Best processing temperature 5 to 30°C. Before use, shake the aerosol.

Distance to the surface to be treated approximately 25 to 30 centimeter.

Apply glue in an equal layer.

For a permanent adhesion, treat both parts to be glued, allow to dry 15 to 20 minutes and firmly press together.

For a temporary adhesion, treat one of the parts to be glued, allow to dry for 5 to 10 minutes and firmly press together.

When treating porous surfaces, apply several layers.

After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).

## **7. SHELF LIFE**

---

10 years in closed packaging and stored in good conditions.

The technical information is in accordance with our experience. We assure the quality of the product. However, the conditions of use are not under our control and we cannot assume any responsibility of the obtained results.