

BOSSAUTO INNOVA, S.A. Pol. Ind. Valldoriolf O' Thomas Edison 16, 08430 La Roca del Vallés. Barcelona t: +34 938 604 923 / f: +34 938 712 336 info@bossauto.com/ www.bossauto.com



TECHNICAL DATA SHEET

1. IDENTIFICATION OF THE PRODUCT AND THE COMPANY

NAME OF THE PRODUCT	U202 Universal black gloss spray 400 ml
CODE	110024
DISTRIBUTOR	BOSSAUTO INNOVA, S.A.
ADDRESS	c/ Thomas Edison 16, Apartado de correos 95
CITY	08430 La Roca del Vallés (Barcelona) SPAIN
PHONE	+ 34 93 860 49 23
FAX	+34 93 871 23 36
E-MAIL	info@bossauto.com
WEB	www.bossauto.com

2. DESCRIPTION OF THE PRODUCT

U202 Universal Black Gloss is a lacquer spray for metals, wood, paper and hard-plastics. It builds up a tough film that has good adhesion. This product has a high gloss when using a well selected alkyd-/acrylic resin combination. The surface gets a protective layer and a completely new look. For good anti-corrosion properties on bare metals, it is recommended the use of a special anti-corrosion primer.

- Yield: 400 ml for 1-2 m²
- Coverage: Dependent on the film thickness: 2 to 3 layers
- Application: Free surface of rust, dirt; let it dry. Cover the parts which should not be painted. Shake the aerosol well before use during 2 to 3 minutes. Spray several thin layers from a distance of approx. 30 cm. Turn the aerosol upside down after use and spray till only gas is coming out.
- Overpaintable: After 10 minutes. After 60 minutes tack-free. Dry within 12 hours. Through hardening takes several days (at 20°C, 40mµ layer).

Resin	Acrylic resin
Pigments	Lead-free
Solids	± 18 % (m/m)
Recommended film thickness	± 75 micron wet, 15-20 micron dry
Gloss	High Gloss (ca 85 GU)
	Gloss measuring angle 60°
Density	± 0.71 – 0.79 Kg/l
Particle size	5-10 micron
Colour	Black
Thinner	DMK

3. TECHNICAL INFORMATION



BOSSAUTO INNOVA, S.A. Pol. Ind. Valldoriolf C/ Thomas Edison 16, 08430 La Roca del Vallés. Barcelona t: +34 938 604 923 / f: +34 938 712 336 info@bossauto.com/ www.bossauto.com



"The information contained herein has been obtained as the result of testing and development work carried out by us. However, this product can be put to numerous uses under widely varying circumstances and conditions and accordingly we do not guarantee the accuracy of the contents of the statements contained herein, and in particular, we do not warrant that this product is suitable for any particular use. We shall not be liable in any way whatsoever to any person who relies upon the statements contained herein without taking sufficient steps to ensure in advance that the product is suitable for this particular purpose, production, conditions and/or use"