

TECHNICAL DATA SHEET

1. IDENTIFICATION OF THE PRODUCT

NAME OF THE PRODUCT	Green washi paper tape
CODE	040056 (19 mm x 50 m) 040057 (28 mm x 50 m) 040058 (38 mm x 50 m) 040059 (50 mm x 50 m)

2. CHARACTERISTICS

Bossauto green washi paper tape is a very high quality, technical and professional product. It is evenly covered by an acrylic adhesive. This can be used for masking general applications. The tape can be applied on most surfaces that are used in the repair of auto bodies. It can also be applied on sharp edges. The tape is resistant to ultraviolet rays and leaves no residue on most surfaces as long as they are removed from the surface during the first 2 months after application.

3. TECHNICAL INFORMATION

Support	61 g/m ² Waterproof Green saturated crepe paper
Adhesive	Water base
Total thickness	0.120 mm
Adhesión to steel	4.1N/25mm
Tensile strength MD	68N/25mm
Praise to the break	8%
Resistance temperature	90°C
Tack – adhesión to the touch	20#-25#

4. APPLICATIONS

Specially designed for cabins, infrared and all types of DIY, essential in the application with any professional paint, whether water or solvent, resulting in a very fine dividing line. Flexible and easy to bend.

5. TECHNICAL CHARACTERISTICS

- Excellent sealing and profiling edges
- For indoor and outdoor use
- All kinds of paintings
- Leaves no residue
- Waterproof
- Ideal for double masks

6. TERMS AND CONDITIONS OF LIABILITY

This tape should be stored in a dry place, protected from direct exposure to sunlight and frost. Storage temperatures should be as close as possible to room temperature. A temperature range of 15 ° C to 25 ° C with a maximum relative humidity of 60% is recommended. Make sure that the surface where the tape is to be placed is clean, dry and free of dust and oils. It is recommended not to apply the tape to temperatures lower than 10°C and to recondition the temperature of the tape at room temperature (15°C to 25°C) before being used.

Shelf life from the date of manufacture: (not yellowing and <10% yield loss at 23 ° C, 50% humidity) is considered to be 12 months.

The technical information is in accordance with our experience. We assure the quality of the product. However, the conditions of use are not under our control and we cannot assume any responsibility of the obtained results.