

BOSSAUTO INNOVA, S.A.

Pol. Ind. Valldoriolf C/Thomas Edison 16, 08430 La Roca del Vallés. Barcelona t: +34 938 604 923 / f: +34 938 712 336 info@bossauto.com / www.bossauto.com



TECHNICAL DATA SHEET

1. IDENTIFICATION OF THE PRODUCT

NAME OF THE PRODUCT Fine line striping tape 130°

CODE 040068 (3 mm x 66 m)

040069 (6 mm x 66 m) 040070 (9 mm x 66 m) 040071 (12 mm x 66 m) 040072 (19 mm x 66 m)

2. DESCRIPTION

This fine line striping tape is flexible and temperature-resistant. It is specially developed for multicolour paint applications of plastic pieces such as bumpers. It is very thin and conforms to the dimensional changes during over-drying or UV drying and it does not shrink or lift off.

It does not leave residues after removal. The flexibility of the base material allows good conformance to multi-dimensional surfaces. It allows wet sanding. It is water-repellent. It can also be used with water-based lacquers.

3. CARRIER

0.11mm PVC copolymer

4. APPLICATION

4.1. Car

- Multi-colour paint applications
- Plastic parts (bumpers...)

4.2. Industry

www.bossauto.com

- Multi-colour paint applications
- Not recommended for outdoor use

4.3. Temperature

Between +15°C and 30°C. Surface must be clean and free from dust and grease. The adhesive must be applied with a maximum pressure in order to achieve its maximum adhesion level. The indicated level of performance will be reached after a bonding period of 24 hours at 23°C.

5. TECHNICAL DETAILS

Adhesion to steel	8.5N/25mm
Tensile Strength	62.5N/25 mm
Elongation (at break)	248%
Temperature resistance	
Long term:	max.100°C
Short term:	max. 150°C

1-2



BOSSAUTO INNOVA, S.A.

Pol. Ind. Valldoriolf C/ Thomas Edison 16, 08430 La Roca del Vallés. Barcelona t: +34 938 604 923 / f: +34 938 712 336 info@bossauto.com / www.bossauto.com



6. STORAGE AND SHELF LIFE

Keep in a clean, dry and well-ventilated area, preferably at a temperature between 10°C and 30°C. Stored under these conditions shelf life will be a minimum of one year.

The technical information is in accordance with our experience. We assure the quality of the product. However, the conditions of use are not under our control and we cannot assume any responsibility of the obtained results.

2-2