

## TECHNICAL DATA SHEET

Updating Date: 22/05/2025

Version: 02/85-4

(\*\*)Indicates changes from the previous version

### SECTION 1. IDENTIFICATION OF THE PRODUCT

**1.1 Product identifier:** **FIBERPLAST Fibreglass 1,8 kg**  
Other forms of identification: **070008**

**1.2 Details of the supplier of the technical data sheet:**

BOSSAUTO INNOVA, S.A.U.  
C/ Londres, 10.  
08401 Granollers, Barcelona – Spain  
t: +34 938 604 923.  
info@bossauto.com.  
<http://www.bossauto.com>.

**1.3 Emergency telephone:** 93 860 49 23 (8:00 - 17:30).

### SECTION 2. DESCRIPTION

This fibreglass filler is perfect for filling irregular and/or deep areas on vehicle bodies. With improved sanding characteristics, it spreads smoothly and evenly, offering very high adhesion on metal substrates (except aluminium and zinc), even on small rust spots.

### SECTION 3. TECHNICAL DATA

<b>Viscosity at 20°C:</b>	As a paste.
<b>VOC content:</b>	2004/42/EG-IIIB;2b(250) <250g/l.
<b>Colour:</b>	Light grey.
<b>Specific weight:</b>	1,78g/ccm.

### SECTION 4. APPLICATION

**Base:**

The base must be clean, dry and grease- free.

Maximum adhesion is achieved on well abraded surfaces such as metal, wood and glassfibre, reinforced body parts based on polyester material.

**Mixing:**

No more than 2-3% (by weight) of Peroxide should be added to 100 parts of tin filler.

Excessive amounts of Peroxide can cause a colour change of the topcoat.

**Pot life:**

Between 3 and 4 minutes at 18-20°C.

**Reaction temperature:**

At least 10°C.

**Applicator:**

Metallic, rubber or plastic spreader.

**Drying time:**

Air drying: 15 or 30 minutes at 18-20°C. Heat will shorten the drying time whereas cold will lengthen it.

**Sanding:**

First sanding: P80 - P120.

Re-sanding: P120 - P240.

---

## **SECTION 5. STORAGE AND SHELF LIFE**

---

Storage at 18-20°C, always in unopened original container. Store in a cool, well-ventilated area away from direct sun light, incompatible materials and ignition sources. Avoid unauthorised access.

If the storage instructions are followed correctly, the shelf life of the product is 12 months.

The technical information is based on our experience. We guarantee the quality of the product; however, as the conditions of use are not under our control, we cannot assume any responsibility for the results obtained.