

# TECHNICAL DATA SHEET

## 1. IDENTIFICATION OF THE PRODUCT AND THE COMPANY

<b>NAME OF THE PRODUCT</b>	GRAVIBOSS HS Undercoating 1L
<b>CODE</b>	070005 (White) 070006 (Grey) 070007 (Black)

## 2. DESCRIPTION






GRAVIBOSS HS is an HS stone chip protector, one-pack component with high benefits. It is ready to use, with a high coating power and without risk of sagging. Its formulation provides a high flexibility finish level, so it is perfect for anticorrosive protection and against hits in low body and wheel arches.

Moreover, it guarantees an optimum soundproofing in applications with a high level of vibration as doors and trunk. Once dried, GRAVIBOSS HS provides an excellent texture or orange-peel effect that allows to be re-painted with bi-layer paints, achieving a perfect bright level.




## 3. PHYSICAL CHARACTERISTICS

Nature	Synthetic resins
Colour	Light grey, dark grey, black, white.
Specific weight	1.5 kg/l at 20°C
Dry film thickness	150-200 microns 1 coat
Yield	5-7 m <sup>2</sup> / kg.
VOC	410 g/l
Solid content	72%

## 4. APPLICATION METHOD

				
Shake before	RB1 schutz gun	3-4 kg/cm <sup>2</sup>	15-25	1-2
using	HP cannister gun	2 kg/cm <sup>2</sup>		

## 5. DRYING

		
10°C	2h	90'
20°C	1,5h	60'
30°C	1h	45'

## **6. REMARKS**

---

The product is ready to use and it does not require additional thinner.

Shake before using.

Apply to grease and rust-free surfaces.

Avoid any mechanical solicitation to the treated parts before 24hours (for example: car wash with high pressure hot water)

Add maximum 20% solvent to obtain a finer finish.

## **7. EQUIPMENT CLEANING**

---

Clean the equipment with a cleaning thinner before of product hardening.

## **8. SAFETY**

---

Follow instructions of product label. For more information check the Safety Data Sheet SDS. Compliant with the National Statutory Regulation for Health and Safety at Work and Waste Disposal.

## **9. STORAGE**

---

Store the product in a ventilated place far from direct exposure to sunlight. Keep between +5°C and +30°C.

## **10. GUARANTEE**

---

In unopened original packaging, one year from manufacturing.

The technical information is in accordance with our experience. We assure the quality of the product. However, the conditions of use are not under our control and we cannot assume any responsibility of the obtained results.