

## TECHNICAL DATA SHEET

### 1. IDENTIFICATION OF THE PRODUCT AND THE COMPANY

---

<b>NAME OF THE PRODUCT</b>	Reusable and calibrated mixing cup 1400 ml TechCup
<b>CODE</b>	100332
<b>DISTRIBUTOR</b>	BOSSAUTO INNOVA, S.A.
<b>ADDRESS</b>	c/ Thomas Edison 16, Apartado de correos 95
<b>CITY</b>	08430 La Roca del Vallés (Barcelona) SPAIN
<b>PHONE</b>	+ 34 93 860 49 23
<b>FAX</b>	+34 93 871 23 36
<b>E-MAIL</b>	<a href="mailto:info@bossauto.com">info@bossauto.com</a>
<b>WEB</b>	<a href="http://www.bossauto.com">www.bossauto.com</a>

### 2. DESCRIPTION

---

Disposable mixing cup for precise preparation of all types of paints. Hermetic seal. Graded scale from 2:1 to 7:1.

### 3. CLOSURE SYSTEM

---

Closure type: Snap-on  
Protective collar: Yes  
Lid type options: Standard lid, Membrane lid  
Container's full capacity: 1400 ml

### 4. ROW MATERIAL

---

Row material options: PP  
Approvals: All products comply with the FDA and European Legislation in force relating to materials and articles intended to come into contact with food.

### 5. STURDINESS

---

The stacking tests have been performed with the standard raw material as stated above at 23°C over a period of 2 months. Stack ability depends on many factors and the above data is meant as an indication only. Consequently, customers should make internal trials to determine the viability of free-standing stacking and transportation. Notably, transparent (CLX) materials are softer than standard material; hence stacking must be considered when contact clear materials are chosen.

### 6. PERFORMANCE

---

#### A. Hot filling

85-95°C

The material chosen has a very good heat resistance and the packaging is suitable for hot filling. Notably, plastic packaging become flexible when subjected to hot filling temperatures and care must be taken in relation to stacking immediately after hot filling. After cooling of the product and pail, the pail regains its original stacking strength.

#### **B. Cold temperatures**

The standard resin material resists temperatures down to -20°C. Standard transparent products might become brittle at temperatures below 0° C.

#### **C. Shelf life**

The compliance of the product to the technical specifications in this data sheet is guaranteed for 12 months after the date of the delivery subject to suitable storage.

#### **D. Quality information**

Deviations in the product specifications in this data sheet of 0.025% or less (i.e. 25 items per 100,000) on a rolling 12 months basis are considered acceptable in the industry and therefore cannot be construed as a defect. Also, please refer to the Standard Sales and Delivery Terms in force at the time of delivery.

The technical information is in accordance with our experience. We assure the quality of the product. However, the conditions of use are not under our control and we cannot assume any responsibility of the obtained results.